

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 02-179390

(43)Date of publication of application : 12.07.1990

(51)Int.Cl.

B23K 35/30
// C22C 5/06

(21)Application number : 01-287651

(71)Applicant : GTE PROD CORP

(22)Date of filing : 06.11.1989

(72)Inventor : MIZUHARA HOWARD

(30)Priority

Priority number : 88 268142 Priority date : 07.11.1988 Priority country : US

(54) SILVER-COPPER-TITANIUM BRAZING ALLOY CONTAINING CRUST INHIBITING ELEMENT

(57)Abstract:

PURPOSE: To prevent a surface crust from being formed in welding a metal and a ceramic by adding a crust inhibiting element of small amount to an alloy for brazing Ag-Cu-Ti of the prescribed composition.

CONSTITUTION: Sn, In of small quantity as elements to prevent the crust during the melting and cooling, and its mixture to a brazing alloy having the composition consisting of, by weight, 0.5-5% Ti, 0.1-approximately 2% Ag, and the balance Cu. As a result, no crust, i.e., a hardened layer is formed even when the brazing alloy is melted on a metal such as stainless steel and kovar (R), and then, cooled to the room temperature. In particular, the quality of the brazing can be improved when the brazing of a metal and a ceramic is requested.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]